

Synthesis and Self-Assembly of Bottlebrush Block Polymers: Molecular Architecture and Materials Design

Thesis by
Alice B. Chang

In Partial Fulfillment of the Requirements
for the Degree of
Doctor of Philosophy

The Caltech logo, featuring the word "Caltech" in a bold, orange, sans-serif font, centered within a light yellow rectangular background.

CALIFORNIA INSTITUTE OF TECHNOLOGY
Pasadena, California

2018
Defended May 25, 2018

© 2018

Alice B. Chang
ORCID: 0000-0001-5036-2681

ACKNOWLEDGMENTS

This thesis represents contributions from many people, including mentors, colleagues, family, and friends. Our interactions have shaped me into the scientist and person I am today, and I would like to thank everyone for their support over the years.

I would first like to thank my advisor, **Prof. Bob Grubbs**. Bob has been a great mentor, and it has been a great privilege to work in his group. One of the lessons Bob teaches is simple but empowering: *don't be afraid to learn new things*. Bob communicates this through his diverse interests and generous support, which have enabled us to pursue the work described in this thesis at the intersection of polymer chemistry and polymer physics. The tremendous depths of Bob's creativity, curiosity, and kindness are truly inspiring. Moving forward, I can only do my best to live up to his support and his example.

I would also like to thank the members of my committee: **Profs. Dave Tirrell, Dennis Dougherty, and Zhen-Gang Wang**. Our conversations and committee meetings have been wonderful opportunities to discuss research directions and explore new ideas. I greatly appreciate their support and insight.

I would next like to thank other members of the Caltech community, starting with the Grubbs group. Thank you for being awesome friends and labmates! Whether we're sharing ideas, chemicals, or memes, you've made the lab a fun and inspiring place to work. I would especially like to thank three former colleagues with whom I worked closely: **Drs. Garret Miyake, Chris Bates, and Tzu-Pin Lin**. Their creativity, expertise, and encouragement have deeply influenced the way I do and think about science.

Garret was my mentor when I first joined the group as a summer (SURF) student, and he introduced me to polymer chemistry and the potential of polymer-based materials. We wrote a review together after I joined the group as a grad student, and I included an overview of the challenges in the field. Garret returned that section unmarked — all discussion of present limitations intact — except he crossed out *challenges* and replaced *opportunities*. I rolled my eyes! However, Garret's edit and enthusiasm echo now when I think about new research directions.

I started to work with Chris during my first year as a grad student, shortly after Chris joined the group as a postdoc. Chris introduced me to polymer physics, and we worked together on several aspects of this thesis, including the phase behavior of low- χ block polymers (Chapter 4) and brush polymer electrolytes (Chapter 6-2). Working with Chris taught me many valuable skills, including how to finish a project and how to write a paper, as well as the value of building diverse interests. At any point, Chris may be reading a textbook on X-ray diffraction or statistical thermodynamics or organic reaction mechanisms, and his creativity in connecting different ideas was inspiring.

TP and I started to work together during my third year as a grad student and TP's first year as a postdoc. TP brought a new perspective and energy to the group, and bouncing ideas back and forth with him was such a fun and rewarding experience. Our backgrounds were different but complementary, enabling us to explore shared interests from multiple angles. Our work together comprises Chapters 2 and 3 of this thesis, describing the synthesis of graft polymers (Chapter 2) and some physical consequences of varying the grafting density and graft distribution (Chapter 3). We once spent several days straight together (including driving 10+ hours to/from a conference) and emerged with new ideas and without hating each other — a real testament to our collaboration!

I was also fortunate to work closely with an exceptional undergrad student, **Shi En Kim**, during her last summer and part of her last year at Caltech. Working with Kim was a real joy — she learned quickly and dug deeply into our work together, and her enthusiasm was inspiring. U Chicago is lucky to have her as a grad student, and I look forward to seeing her accomplish great things.

I have been fortunate to work with several other members of the Grubbs group, and I appreciate their contributions to the work described in this thesis. **Shao-Xiong (Lennon) Luo** was a very talented undergrad who contributed to the monomer synthesis and copolymerization kinetics described in Chapter 2. **Drs. Crystal Chu, Pablo Guzmán, Allegra Liberman-Martin, Rob Macfarlane**, and I explored various approaches to block polymer photonic crystals (Chapter 6-1). **Brendon McNicholas** and **Nebo Momčilović** played important roles in the brush polymer electrolyte studies described in Chapter 6-2.

The work presented in this thesis has benefited from the contributions of many other members of the Caltech community. **Dr. Hsiang-Yun Chen** and **Niklas Thompson** have made key contributions to our studies of ROMP kinetics: Hsiang-Yun wrote the code to fit our copolymerization data and calculate reactivity ratios (Chapter 2-4), and Nik performed density functional theory (DFT) calculations to provide insight into the ROMP mechanism (Chapter 2-9). I would like to thank **Prof. Jonas Peters** for providing access to computational resources. I would also like to thank **Prof. Julie Kornfield** and her student, **Joey Kim**, for access to their rheometer and for valuable discussions. In addition, I would like to thank **Prof. Zhen-Gang Wang** and members of his group, including **Prof. Liquan Wang**, **Dr. Pengfei Zhang**, and **Dr. Jian Jiang**, for their patience in discussing self-consistent field theory (SCFT) and polymer phase behavior with me. Liquan, with input from Pengfei and JJ, built SCFT up from scratch in his explanations, and our conversations helped me gain a deeper appreciation for the theory.

The Caltech instrument facilities have been great resources. **Dr. Dave VanderVelde** keeps the NMR facility in shipshape, and I have learned a lot from him (and his coffee and beer posters!). **Dr. Mona Shahgholi** has helped me answer tough questions about polymer composition by mass spectrometry. **Dr. Chi Ma** trained me to operate the scanning electron microscope and has helped troubleshoot many samples since. **Mark Ladinsky** and **Dr. Alasdair McDowall** trained me to use the cryomicrotome in the bio-imaging facility; in addition, Mark microtomed several of the brush triblock samples discussed in Appendix C. I would especially like to thank **Carol Garland** for teaching me and working with me to image samples by transmission electron microscopy (TEM). Her help was invaluable in obtaining the TEM images in Chapter 4, which first alerted us to the unusual mesoscopic domain connectivity in these low- χ materials.

We have been tremendously fortunate to collaborate with members of the scientific community outside Caltech. Their contributions have crucially enabled the work presented in this thesis. I would like to express my deep appreciation for their expertise and insight, as well as my sincere hope that we will continue to find opportunities to collaborate. I will thank our collaborators in the approximate order of the first appearance of their contributions in this thesis.

My first acknowledgment must be to **Dr. Byeongdu Lee**, a beamline scientist at Argonne National Laboratory's Advanced Photon Source and a leader in the X-ray scattering community. We started to work together during my second year of grad school, and I have since learned everything I know about scattering — and most of what I know about polymer physics — from Byeongdu. In addition to providing technical support at the beamline, Byeongdu has played a key role in our work to interpret the influences of the graft polymer architecture on block polymer phase behavior. His contributions are reflected in almost every chapter of this thesis, including our models for the scaling of the lamellar period with grafting density (Chapter 3-2), the role of screening in low- χ materials (Chapter 4), and crystallization in brush block polymers (Chapter 5-3).

I would also like to thank our collaborators at the University of Minnesota: **Ingrid Haugan, Dr. Michael Maher, Prof. Marc Hillmyer, and Prof. Frank Bates**. They performed the studies described in Chapter 3-3 to explore the effects of grafting density on linear rheological properties. I greatly appreciate the opportunity to learn more about rheology and these materials through their efforts. I would additionally like to thank Frank for his valuable suggestions regarding partial mixing in our low- χ brush block polymers (Chapter 4), as well as **Drs. Sid Chanpuriya, Matt Irwin, and Tuoqi Li** for their assistance with microtomy.

Dr. Simon Jones at the Jet Propulsion Laboratory, in addition to **Prof. Christina Bauer** and her student **Matt Voegtle** at Whittier College, helped us obtain differential scanning calorimetry (DSC) data. DSC data was an important part of our studies of various systems, including the graft copolymers in Chapter 2-3, the brush LSO and LSL' triblocks in Chapter 4, and the solid polymer electrolytes in Chapter 6-2.

Prof. Mark Matsen at the University of Waterloo played a key role in our work studying the effects of low- χ block polymer design (Chapter 4). His SCFT calculations helped guide our molecular interpretation of the unusual phase behavior. In this and several other contexts, Mark was immediately ready with a compelling explanation — and not only an explanation, but a relevant reference from his previous work! I appreciate his insight and, through our work together, the opportunity to see how simulations can help build physical models.

I would next like to thank our collaborators at the National Institute of Standards and Technology (NIST): **Drs. Adam Burns, Dean DeLongchamp, Chris Soles, and Dan Sunday**. Adam and Chris are studying the dynamics and conformations of our graft polymers via neutron scattering (not included in this thesis). Chris, Dean, and Dan performed the resonant soft X-ray reflectivity (RSoXR) measurements and interpretation described in Chapter 4-10, which provided new insights into the LAMP structure and its demands on the bottlebrush architecture. We started to work together after Chris and I met at a conference and Chris suggested reflectivity measurements. I had never heard of the technique, and I certainly could not have imagined how powerful it can be! Working with Adam, Dean, Chris, and Dan has been great fun and a great introduction to new characterization techniques. I greatly appreciate the opportunities to collaborate.

Lastly, I would like to thank my friends and family. **Alexis Kurmis** and I were roommates during our first two years at Caltech, as well as friends from college. Sunday dinners with Alexis really helped Caltech feel like home, and they are among my favorite parts of grad school. The Grubbs group has been full of some of the greatest people and friends I have ever met. In addition to being wonderful collaborators, Garret, Chris, TP, Kim, and Pablo are good friends. **Crystal Chu** knows all the best Asian food in the LA area, and late-night boba or noodle runs were great de-stressors. Exploring Pasadena and hanging out with Crystal, **Jae Engle, Keary Engle, Natalie Khuen, Rob Macfarlane, Hans Renata, and Zach Wickens** are among my best memories of the first years of grad school. Looking forward to a reunion fried chicken crawl someday! I still listen to **Ray Weitekamp's** ingMob album sometimes. Coffee and conversations with **Julian Edwards, Sankar Krishnamoorthy, Allegra Liberman-Martin, Karthish Manthiram, Chris Marotta, and Willie Wolf** have been a lot of fun. Thanks for the cheese danishes, Julian!

Mom, Dad, and Oliver — thank you for all your love and support. Gumshoe adventures and library trips are some of the earliest things I remember, and everything since has been inspired by you. Thank you to the **Cialdella family** for welcoming me, and for all your warmth (and wine!). Last but not least, **Louis** — thank you for being here for it all. Thank you for making first New York and now LA home. Thank you for making me coffee and making me laugh. I'm looking forward to the next adventure.

ABSTRACT

Bottlebrush polymers represent a unique molecular architecture and a modular platform for materials design. However, the properties and self-assembly of bottlebrush polymers remain relatively unexplored, in large part due to the synthetic challenges imposed by the sterically demanding architecture. This thesis describes our work to close this gap, connecting (1) the synthesis of polymers with precisely tailored molecular architectures, (2) the study of fundamental structure-property relationships, and (3) the design of functional materials.

Chapter 1 introduces key concepts related to polymer architecture and block polymer phase behavior. Recent developments in the synthesis and self-assembly of bottlebrush block polymers are highlighted in order to frame the work presented in Chapters 2–6.

Chapter 2 introduces a versatile strategy to design polymer architectures with arbitrary side chain chemistry and connectivity. Simultaneous control over the molecular weight, grafting density, and graft distribution can be achieved via living ring-opening metathesis polymerization (ROMP). Copolymerizing a macromonomer and a small-molecule co-monomer provides access to well-defined polymers spanning the linear, comb, and bottlebrush regimes. This design strategy creates new opportunities for molecular and materials design.

Chapter 3 explores the physical consequences of varying the grafting density and graft distribution in two contexts: block polymer self-assembly and linear rheological properties. The molecular architecture strongly influences packing demands and therefore the conformations of the backbone and side chains. Collectively, these studies represent progress toward a universal model connecting the chemistry and conformations of graft polymers.

Chapter 4 discusses the phase behavior of ABA' and ABC bottlebrush triblock terpolymers. Low- χ interactions between the end blocks promote organization into a unique mixed-domain lamellar morphology, LAMP. X-ray scattering experiments reveal an unusual trend: the domain spacing strongly *decreases* with increasing total molecular weight. Insights

into this behavior provide new opportunities for block polymer design with potential consequences spanning all self-assembling soft materials.

Chapter 5 describes other physical consequences of low- χ block polymer design. The ternary phase diagrams for ABC, ACB, and BAC bottlebrush triblock terpolymers reveal the influences of low- χ A/C interactions, frustration, and the molecular architecture. Potential non-equilibrium effects and crystallization in these bottlebrush polymers will also be discussed.

Chapter 6 describes applications of bottlebrush polymers as functional materials. Self-assembly enables mesoscale structural control over many materials properties, such as reflectivity, conductivity, and modulus. The synthetic methods (Chapter 2) and physical insights (Chapters 3–5) provided in previous chapters illustrate opportunities for materials design. We will discuss AB brush diblock polymers that self-assemble to photonic crystals and ABA brush triblock copolymers in solid polymer electrolytes.

PUBLISHED CONTENT AND CONTRIBUTIONS

The work in this thesis includes content from the following published or submitted manuscripts. This work was enabled by the contributions of all authors, which are described in the acknowledgments and reflected throughout the thesis. In the interest of brevity, only contributions by A.B.C. have been identified below, except where appropriate to acknowledge other authors in the same role.

Chapter 2: Control over the Graft Polymer Architecture via Ring-Opening Metathesis Polymerization

1. Lin, T.-P.; Chang, A. B.; Chen, H.-Y.; Liberman-Martin, A. L.; Bates, C. M.; Voegtle, M. J.; Bauer, C. A.; Grubbs, R. H. Control of Grafting Density and Distribution in Graft Polymers by Living Ring-Opening Metathesis Copolymerization. *J. Am. Chem. Soc.* **2017**, *139*, 3896–3903. doi: 10.1021/jacs.7b00791.

A.B.C. designed the study (with T.-P.L. and C.M.B.), performed some of the macromonomer synthesis and homo- and copolymerization experiments, interpreted data, and contributed to manuscript preparation.

2. Chang, A. B.,⁺ Lin, T.-P.,⁺ Thompson, N. B.; Luo, S.-X.; Liberman-Martin, A. L.; Chen, H.-Y.; Grubbs, R. H. Design, Synthesis, and Self-Assembly of Polymers with Tailored Graft Distributions. *J. Am. Chem. Soc.* **2017**, *139*, 17683–17693. doi: 10.1021/jacs.7b10525. (⁺*Equal contributions.*)

A.B.C. designed the study, performed some of the macromonomer synthesis and homo- and copolymerization experiments, collected and analyzed X-ray scattering data, interpreted data, and wrote the paper.

Chapter 3: Impacts of the Graft Polymer Architecture on Physical Properties

3. Lin, T.-P.,⁺ Chang, A. B.,⁺ Luo, S.-X.; Chen, H.-Y.; Lee, B.; Grubbs, R. H. Effects of Grafting Density on Block Polymer Self-Assembly: From Linear to Bottlebrush. *ACS Nano* **2017**, *11*, 11632–11641. doi: 10.1021/acsnano.7b06664. (⁺*Equal contributions.*)

A.B.C. designed the study, collected and analyzed X-ray scattering data, imaged materials by scanning electron microscopy, proposed a model for the observed scaling of the block polymer lamellar period (with B.L.), and wrote the paper (with T.-P.L.).

4. Haugan, I. N.; Maher, M. J.; Chang, A. B.; Lin, T.-P.; Grubbs, R. H.; Hillmyer, M. A.; Bates, F. S. Consequences of Grafting Density on the Linear Viscoelastic Behavior of Graft Polymers. *ACS Macro Lett.* **2018**, *7*, 525–530. doi: 10.1021/acsmacrolett.8b00116.

A.B.C. contributed to the conception of the project (with all other authors), synthesized all graft polymer samples, and contributed to manuscript preparation.

Chapter 4: Manipulating the ABCs of Self-Assembly via Low- χ Block Polymer Design

5. Chang, A. B.; Bates, C. M.; Lee, B.; Garland, C. M.; Jones, S. C.; Spencer, R. K.; Matsen, M. W.; Grubbs, R. H. Manipulating the ABCs of Self-Assembly via Low- χ Block Polymer Design. *Proc. Natl. Acad. Sci.* **2017**, *114*, 6462–6467. doi: 10.1073/pnas.1701386114.

A.B.C. designed the study, coordinated with all collaborators, synthesized all polymers, collected and analyzed X-ray scattering data (with B.L.), imaged materials by transmission electron microscopy, interpreted data, proposed a model for the unusual domain spacing trends (with C.M.B., B.L., and M.W.M.), and wrote the paper (with C.M.B.).

6. Sunday, D. F.;* Chang, A. B.;* Liman, C. D.; Gann, E.; DeLongchamp, D. M.; Matsen, M. W.; Grubbs, R. H.; Soles, C. L. Evidence for Backbone Flexibility of Bottlebrush Block Copolymers Driven by Low- χ Assembly. **2018**. *submitted*. (*Corresponding authors.)

A.B.C. contributed to the conception of the project (with C.L.S.), synthesized all polymers, prepared thin films for reflectivity measurements, imaged materials by atomic force microscopy, proposed a model for the observed relative domain thicknesses (with D.F.S. and M.W.M.), contributed to manuscript preparation, and serves as co-corresponding author (with D.F.S.).

Chapter 6: Applications of Bottlebrush Polymers in Functional Materials

7. Macfarlane, R. J.; Kim, B.; Lee, B.; Weitekamp, R. A.; Bates, C. M.; Lee, S. F.; Chang, A. B.; Delaney, K. T.; Fredrickson, G. H.; Atwater, H. A.; Grubbs, R. H. Improving Brush Polymer Infrared One-Dimensional Photonic Crystals via Linear Polymer Additives. *J. Am. Chem. Soc.* **2014**, *136*, 17374–17377. doi: 10.1021/ja5093562.

A.B.C. imaged all samples by scanning electron microscopy and provided edits to the manuscript.

8. Bates, C. M.; Chang, A. B.; Momčilović, N.; Jones, S. C.; Grubbs, R. H. ABA Triblock Brush Polymers: Synthesis, Self-Assembly, Conductivity, and Rheological Properties. *Macromolecules* **2015**, *48*, 4967–4973. doi: 10.1021/acs.macromol.5b00880.

A.B.C. synthesized some of the macromonomers and brush polymers, collected and analyzed some of the rheology and X-ray scattering data, and contributed to manuscript preparation.

9. Bates, C. M.; Chang, A. B.; Schulze, M. W.; Momčilović, N.; Jones, S. C.; Grubbs, R. H. Brush Polymer Ion Gels. *J. Polym. Sci., Part B* **2016**, *54*, 292–300. doi: 10.1002/polb.23927.

A.B.C. synthesized some of the macromonomers and brush polymers, collected and analyzed some of the rheology and X-ray scattering data, and contributed to manuscript preparation.

10. McNicholas, B. J.; Blakemore, J. D.; Chang, A. B.; Bates, C. M.; Kramer, W. W.; Grubbs, R. H.; Gray, H. B. Electrocatalysis of CO₂ Reduction in Brush Polymer Ion Gels. *J. Am. Chem. Soc.* **2016**, *138*, 11160–11163. doi: 10.1021/jacs.6b08795.

A.B.C. synthesized the polymers, collected and analyzed X-ray scattering data, and provided edits to the manuscript.

TABLE OF CONTENTS

Acknowledgments	iii
Abstract	viii
Published Content and Contributions.....	x
Table of Contents.....	xiii
List of Figures and Schemes.....	xvi
List of Tables	xxxiii

Chapter 1: Introduction

1-1 Molecular Architecture	1
1-2 Bottlebrush Polymer Synthesis.....	5
1-3 Block Polymer Self-Assembly	11
1-4 Thesis Outline	14
1-5 References	15

Chapter 2: Control over the Graft Polymer Architecture via Ring-Opening Metathesis Polymerization

Abstract	19
2-1 Introduction	20
2-2 Monomer Design.....	23
2-3 Homopolymerization Kinetics.....	24
2-4 Developing an Analytical Method for Copolymerization Kinetics.....	26
2-5 Copolymerization Kinetics	28
2-6 Instantaneous Copolymer Composition	34
2-7 Synthesis of Architectures with Variable Grafting Density	35
2-8 Expanding Monomer Design.....	37
2-9 Origin of Rate Trends	42
2-10 Copolymerization Kinetics	45
2-11 Tuning Graft Polymer Architecture.....	48
2-12 Conclusion.....	52
2-13 References	53

Chapter 3: Impact of the Graft Polymer Architecture on Physical Properties

Abstract	57
3-1 Impact of Graft Distribution on Block Polymer Self-Assembly	58
3-2 Impact of Grafting Density on Block Polymer Self-Assembly	63
3-2.1 Introduction.....	63
3-2.2 Synthesis of Block Polymers with Variable Grafting Density (System I)..	64
3-2.3 Self-Assembly and Scaling of the Lamellar Period.....	67
3-2.4 Synthesis and Self-Assembly: System II	69

3-2.5 Interpretation of the Scaling Trends.....	73
3-3 Impact of Grafting Density on Linear Rheology	80
3-4 References	87

Chapter 4: Manipulating the ABCs of Self-Assembly via Low- χ Block Polymer Design

Abstract	91
4-1 Introduction	92
4-2 Synthesis and Structure of Low- χ Block Polymers	93
4-3 Self-Consistent Field Theory	96
4-5 Decreasing Domain Spacing with Increasing Total Molecular Weight.....	99
4-6 Role of Low- χ Interactions	101
4-7 Molecular Asymmetry Effects.....	103
4-8 Screening Unfavorable Block-Block Interactions	105
4-9 Dispersity and Architecture	106
4-10 Evidence for Backbone Flexibility	107
4-11 Conclusions	117
4-12 References	117

Chapter 5: Consequences of Low- χ Block Polymer Design: Phase Behavior, Equilibrium, and Crystallization

Abstract	120
5-1 Ternary Phase Behavior.....	121
5-1.1 LSO Brush Triblock Terpolymers	121
5-1.2 SLO and LOS Brush Triblock Terpolymers.....	127
5-2 Potential Non-Equilibrium Behavior.....	129
5-3 Crystallization	132
5-3.1 Crystallization and Domain Spacing Trends	132
5-3.2 Crystallization Kinetics	133
5-3.3 Confined Crystallization and Chain Orientation	140
5-4 References	146

Chapter 6: Applications of Bottlebrush Block Polymers in Functional Materials

Abstract	148
6-1 Photonic Crystals	149
6-1.1 Introduction.....	149
6-1.2 Grafting Density	152
6-1.3 Discrete Monomers.....	153
6-1.4 Blends with Linear Homopolymers	156
6-2 Solid Polymer Electrolytes	161
6-2.1 Introduction.....	161
6-2.2 Blends with Lithium Salt.....	163
6-2.3 Brush Polymer Ion Gels	168
6-3 References	173

Appendix A: Appendix to Chapter 2

A-1	Instrumentation	179
A-2	Macromonomer Synthesis	179
A-2.1	Synthesis of Poly(D,L-lactide) Macromonomer (PLA)	179
A-2.2	Synthesis of Polystyrene Macromonomer (PS)	182
A-2.3	Synthesis of Poly(dimethyl siloxane) Macromonomer (PDMS)	185
A-2.4	Synthesis of Poly(ethylene oxide) Macromonomer (PEO)	187
A-3	Diluent Synthesis	188
A-4	Standard Procedures for Homo- and Copolymerization Kinetics	191
A-4.1	Standard Procedure for Homopolymerization	191
A-4.2	Standard Procedure for Copolymerization	191
A-5	Characterization of (PLA ^z - <i>ran</i> -DME ^{1-z}) _n Graft Polymers	192
A-6	Expanding Monomer Scope: Homopolymerization Rate Constants	194
A-7	Mechanistic Studies	195
A-7.1	Pyridine Binding	195
A-7.2	Derivation of Rate Expression (Eq. 2-8)	196
A-7.3	Rate Dependence on Catalyst Concentration	197
A-8	Copolymerization Kinetics Data	198

Appendix B: Appendix to Chapter 3

B-1	Characterization	203
B-1.1	Instrumentation	204
B-1.2	Determination of Grafting Density by ¹ H NMR	205
B-1.3	Determination of <i>N</i> _{bb} by SEC	207
B-2	Supporting Data: Graft Distribution and Block Polymer Self-Assembly	208
B-3	Supporting Data: Grafting Density and Block Polymer Self-Assembly	209
B-4	Supporting Data: Grafting Density and Linear Rheology	219

Appendix C: Appendix to Chapter 4

C-1	Synthesis of LSO and LSL' Brush Triblock Polymers	222
C-2	Molecular Characterization	225
C-2.1	Instrumentation: ¹ H NMR and SEC	225
C-2.2	Characterization of LSO and LSL' Triblock Polymers	225
C-3	Self-Consistent Field Theory (SCFT): Methods	228
C-4	Transmission Electron Microscopy (TEM)	230
C-5	Small-Angle X-ray Scattering (SAXS)	232
C-6	Supporting Data for LSO- <i>N</i> _C Series	233
C-7	Supporting Data for LSL'- <i>N</i> _{A'} Series	239
C-8	Differential Scanning Calorimetry (DSC)	244
C-9	SCFT Calculations: LSO- <i>N</i> _C and LSL'- <i>N</i> _{A'} Series	246
C-10	Wide-Angle X-ray Scattering (WAXS)	248

LIST OF FIGURES AND SCHEMES

Figure 1.1:	Comparison of linear (<i>left</i>) and bottlebrush (<i>right</i>) polymer architectures. For a fixed monomer chemistry, the linear polymers feature one independent structural parameter: the total degree of polymerization, N . In contrast, bottlebrush polymers must be described by multiple parameters, including the backbone length (N_{bb}), side chain length (N_g), grafting density ($z = 1/N_g$), and graft distribution.	2
Figure 1.2:	(A) Diagram of states for graft polymers based on the side chain degree of polymerization (N_{sc}) and inverse grafting density ($N_g = 1/z$). Loose comb (LC), dense comb (DC), loose brush (LB), and dense brush (DB) regimes are anticipated by theory. The conformations of the side chains and backbone vary in each regime. (B) Predicted entanglement plateau modulus of graft polymer melts ($G_{e,graft}$) relative to linear polymer melts ($G_{e,linear}$) as a function of N_{sc} . The normalized modulus decreases with increasing N_{sc} , and the scaling exponent changes in each regime.	4
Figure 1.3:	Three routes to bottlebrush polymers. (A) Grafting-to strategies attach monotelechelic chains to a pre-formed polymer backbone. (B) Grafting-from strategies grow side chains from a pre-formed macroinitiator. (C) Grafting-through strategies polymerize macromonomers in order to grow the brush through the backbone.....	6
Scheme 1.1:	Mechanism of ring-opening metathesis polymerization (ROMP). In well-defined catalysts, the metal center (M) is tungsten, molybdenum, or ruthenium.....	8
Figure 1.4:	Living grafting-through ROMP of ω -norbornenyl macromonomers mediated by the fast-initiating G3 catalyst. Macromonomers are stitched together through the backbone, providing access to well-defined bottlebrush polymers.....	9
Figure 1.5:	Opportunities for architectural design via living grafting-through ROMP. Schematic illustrations of polymer architectures are provided on the left. For ease of visualization, the polymers are illustrated in the limit of fully extended backbones, and cylinders indicate the anticipated local cross-sectional radii of gyration. Red and blue side chains indicate different chemical compositions (<i>i.e.</i> , Block A and Block B, respectively). For each row (B–F), the architectural variation compared to the previous row (<i>second to last column</i>) and required synthetic change (<i>last column</i>) are provided.	10
Figure 1.6:	Equilibrium morphologies observed linear AB diblock polymers, the simplest polymer architecture.	12

- Figure 1.7:** Compiled reported examples of the scaling of the lamellar period (d^*) with the backbone length (N_{bb}) for six series of bottlebrush diblock polymers. All polymers are fully grafted and feature symmetric PLA and PS side chains. The average side chain molecular weights (M_{sc} , in kDa) are provided in the legend. The letters in parentheses indicate the corresponding reference: (A) = Ref. 17, (B) = Ref. 94, (C) = Ref. 96, and (D) = Ref. 97. A dotted line corresponding to $\alpha = 0.90$ is included for comparison. 13
- Figure 1.8:** Self-assembly of (A) linear and (B) bottlebrush diblock polymers to lamellar morphologies. The scaling of the lamellar period with backbone degree of polymerization ($d^* \sim N_{bb}^\alpha$) differs as a consequence of the molecular architecture. 14
- Figure 2.1:** Grafting-through ROMP of a small-molecule diluent (*white*) and a macromonomer (*black*). Since the side chains (*red*) are connected to certain backbone units, control over the backbone sequence directly determines the side chain distribution: (A) uniform, (B) gradient, etc. The anticipated average cross-sectional radius of gyration (R_c) is indicated. For ease of visualization, chains are illustrated in the limit of fully extended backbones. 18
- Figure 2.2:** (*left*) Structures of macromonomers (**PS**, **PLA**, **PDMS**) and diluents (**DME**, **DEE**, **DBE**). (*right*) Plots of $\ln([M]_0/[M]_t)$ versus time, showing first-order kinetics for the homopolymerization of norbornene monomers (0.05 M) catalyzed by **G3** (0.5 mM) in CH_2Cl_2 at 298 K (orange stars: **PDMS**, inverted red triangles: **DME**, green squares: **PLA**, brown diamonds: **DEE**, purple triangles: **DBE**, blue circles = **PS**). The numbers in parentheses indicate k_{obs} (10^{-3} s^{-1}) under the reaction conditions. 20
- Figure 2.3:** Representative repeated runs to determine k_{homo} ($\text{M}^{-1} \text{ s}^{-1}$) for (A) **DME** and (B) **PLA**. For all diluents and macromonomers studied herein, the measured rate constants are consistent across multiple runs. 21
- Scheme 2.1:** Propagation reactions for the copolymerization of a discrete diluent (M_2 , *dx*-DE shown for example) and a macromonomer (M_1) according to a terminal model. M_2^* and M_1^* are the corresponding propagating alkylidene species. (A) Diluent self-propagation (k_{22}), (B) cross-propagation (k_{21}), (C) macromonomer self-propagation (k_{11}), (D) cross-propagation (k_{12}). 22
- Scheme 2.2:** Mayo-Lewis terminal model describing the copolymerization of M_1 and M_2 23
- Figure 2.4:** (A) Copolymerization of **PS** (0.05 M) and **DME** (0.05 M) catalyzed by **G3** (0.5 mM) in CH_2Cl_2 at 298 K. (B) Normalized differential refractive index (dRI) trace from size-exclusion chromatography. (C) Plots of $\ln([M]_0/[M]_t)$ versus time as monitored by ^1H NMR spectroscopy (filled

- blue circles = **PS**, filled red triangles = **DME**). Unfilled blue circles (**PS**), unfilled red triangles (**DME**), and the solid lines, plotted for comparison, were obtained from homopolymerization reactions under the same conditions. 25
- Figure 2.5:** Non-linear least-square curve fitting for the copolymerization of (A, B) **PS** (0.05 M) and **DME** (0.05 M) and (C, D) **PS** (0.05 M) and **DME** (0.10 M) in CH₂Cl₂ at 298 K. [G3]₀ = 0.5 mM. Calculated fits (solid lines) show close agreement with the measured values (points). In (B, D), the dashed lines, included for comparison, indicate ideal random copolymerization ($r_1 = r_2 = 1$). 27
- Figure 2.6:** Non-linear least-square curve fitting for the copolymerization of various macromonomer/diluent pairs: (A, B) **PS** (0.05 M) and **DEE** (0.05 M); (C, D) **PS** (0.05 M) and **DBE** (0.05 M); (E, F) **PS** (0.075 M) and **DBE** (0.025 M). [G3]₀ = 0.5 mM, solvent = CH₂Cl₂, temperature = 298 K. 28
- Figure 2.7:** Non-linear least-square curve fitting for the copolymerization of various macromonomer/diluent pairs: (A, B) **PLA/DME**; (C, D) **PLA/DBE**; (E, F) **PDMS/DME**; (G, H) **PDMS/DBE** (0.055 M). Reaction conditions: [M]₀ = 0.05 M unless otherwise indicated, [G3]₀ = 0.5 mM, solvent = CH₂Cl₂, temperature = 298 K. 30
- Figure 2.8:** Simulated copolymer composition for (A) **PS:DME** = 1:1, (B) **PLA:DME** = 1:1, (C) **PDMS:DME** = 1:1, and (D) **PDMS:DBE** = 1:1. Insets show schematic illustrations of the corresponding graft polymers; for ease of visualization, the side chains and backbones are shown in the fully extended limit. 31
- Figure 2.9:** SEC traces of (PLA^{z-ran}-DME^{1-z})_n where z = grafting density (1.0, 0.75, 0.50, or 0.25) and n = total backbone degree of polymerization (red: 167, orange: 133, green: 100, blue: 67, purple: 33). 32
- Figure 2.10:** Homopolymerization rate constants (k_{homo}) for substituted *endo,exo*-norbornenyl diester monomers (left to right: **1a–j**). k_{homo} decreases with increasing steric bulk (R = Me to ^tBu, **1a–f**). k_{homo} does not change significantly with electronic changes via fluorination (**1g**) or *para*-substitution of a phenyl ring (**1h–j**). 35
- Scheme 2.3:** Expanding the scope of monomer design for ring-opening metathesis copolymerization. 33
- Figure 2.11:** (A) Homopolymerization rate constants (k_{homo}) for monomers with *exo,exo*-diester (*xx*, green), *endo,exo*-diester (*dx*, red), and *endo,endo*-diester (*dd*, yellow) anchor groups. Comparison of k_{homo} for monomers with R = Me, Et, ⁿPr, and ⁿBu supports the steric influences of stereochemistry and substituent size. (B) k_{homo} for Me- and ⁿBu-substituted monomers with each of the five anchor groups; *endo*-imide (*d-I*, blue) and *exo*-imide (*x-I*, purple). 36

- Figure 2.12:** Plot of k_{homo} values for all monomers studied herein. The monomers are sorted according to their anchor groups: *left to right*: *endo,exo*-diester (red, **1a–j**), *endo,endo*-diester (yellow, **2a–d**), *exo,exo*-diester (green, **3a–d**), *endo*-imide (blue, **4a–c**), and *exo*-imide (purple, **5a–c** and macromonomers). k_{homo} values for methyl-substituted monomers are provided for comparison. 37
- Figure 2.13:** Proposed dissociative ROMP pathway for **G3**. The DFT-optimized structures of three catalytically relevant ruthenium catalyst species are shown: (A) six-membered Ru–O chelate, (B) 14-electron vacant species, and (C) olefin adduct. 39
- Figure 2.14:** DFT-calculated free energy diagram corresponding to one ROMP cycle for *endo*- (**2a**, blue) and *exo*-substituted (**3a**, red) norbornenyl monomers. The following intermediates were calculated: (A) six-membered Ru–O chelate, (B) 14-electron vacant species, (C) olefin adduct, and (D) metallacyclobutane. See also Figure 2.13. 40
- Figure 2.15:** (A) Copolymerization scheme: the same macromonomer (**PLA**, M_1) was copolymerized with 13 different diluents (M_2). The feed ratio ($x/y = 1$) and total backbone length ($x + y = 200$) were fixed. (B) M_2 arranged in order of increasing k_{22} 42
- Figure 2.16:** SEC traces for **PLA** + diluent copolymerizations at full conversion. 42
- Figure 2.17:** **PLA**/diluent copolymerization data. Left axis, black: self-propagation rate constants (k_{22} : filled circles, k_{11} : open circles). Right axis, red: reactivity ratios (r_2 : solid line, r_1 : dotted line). 43
- Figure 2.18:** Simulated sequences and (inset) graft polymer architectures for the copolymerization of **PLA** with different diluents: (A) **4a**, (B) **1a**, or (C) **5a**. For ease of visualization, the simulated structures show fully extended side chains and backbones. 45
- Figure 2.19:** Data for the copolymerization of $M_1 = \text{PDMS}$ (left) or **PS** (right) with different diluents. Left axis, black: self-propagation rate constants (k_{22} : filled circles, k_{11} : open circles). Right axis, red: reactivity ratios (r_2 : solid line, r_1 : dotted line). 46
- Figure 2.20:** Reactivity ratio map. The copolymerization kinetics studied for **PLA**, **PDMS**, and **PS** are interpreted in terms of the quotient r_1/r_2 , plotted on the x-axis. For ease of visualization, the simulated structures show fully extended side chains and backbones. 47
- Scheme 3.1:** Illustrations of three AB graft diblock polymers differing only in the side chain distribution: (A) uniform (**BP-1**), (B) gradient (**BP-2**), and (C) inverse-gradient (**BP-3**). (top) Chemical structures. (bottom) Schematic illustrations of the anticipated molecular “shapes,” shown in the limit of fully extended backbones for ease of visualization. 59

- Figure 3.1:** SAXS patterns corresponding to the annealed graft block polymers: (A) **BP-1**, (B) **BP-2**, (C) **BP-3**. The white “x” indicates the first-order diffraction peak, q^* 61
- Figure 3.2:** Schematic illustration of the relationships between chain dimensions and the lamellar period. (A) $d_A \approx 3d_B$ is expected if the backbones are fully stretched (since $N_{bb,A} = 3N_{bb,B}$), but it is consistent with SAXS data. (B) Instead, $d_A \approx d_B$ is observed. This requires bending of the A block backbone. (C) Illustration of **BP-3** and revised chain conformations. 61
- Figure 3.3:** Comparison of simulated (*top, middle*) and measured (*bottom*) 1D-averaged SAXS data. The experimental data closely matches the expected SAXS pattern corresponding to lamellae with symmetric ($d_A = d_B$) domains. 62
- Figure 3.4:** Self-assembly of linear and bottlebrush diblock polymers into lamellae. 63
- Scheme 3.2:** Synthesis of $(\text{PLA}^z\text{-}r\text{-DME}^{1-z})_n\text{-}b\text{-}(\text{PS}^z\text{-}r\text{-DBE}^{1-z})_n$ block polymers (**System I**) featuring variable backbone degrees of polymerization ($N_{bb} = 2n = 44\text{--}363$) and grafting densities ($z = 1.00, 0.75, 0.50, 0.35, 0.25, 0.20, 0.15, 0.05, 0$)..... 65
- Figure 3.5:** Scanning electron micrographs of graft block polymers with (A) $z = 1.00$, $(\text{PLA})_{100}\text{-}b\text{-}(\text{PS})_{100}$; (B) $z = 0.75$, $(\text{PLA}^{0.75}\text{-}r\text{-DME}^{0.25})_{110}\text{-}b\text{-}(\text{PS}^{0.75}\text{-}r\text{-DBE}^{0.25})_{110}$; (C) $z = 0.50$, $(\text{PLA}^{0.5}\text{-}r\text{-DME}^{0.5})_{104}\text{-}b\text{-}(\text{PS}^{0.5}\text{-}r\text{-DBE}^{0.5})_{104}$; and (D) $z = 0.25$, $(\text{PLA}^{0.25}\text{-}r\text{-DME}^{0.75})_{112}\text{-}b\text{-}(\text{PS}^{0.25}\text{-}r\text{-DBE}^{0.75})_{112}$ 68
- Figure 3.6:** (*top*) Scheme of **System I**, comprising graft block polymers $(\text{PLA}^z\text{-}r\text{-DME}^{1-z})_n\text{-}b\text{-}(\text{PS}^z\text{-}r\text{-DBE}^{1-z})_n$ with variable total backbone degrees of polymerization ($N_{bb} = 2n$) and grafting densities (z). (A) Stacked 1D azimuthally averaged SAXS profiles for $z = 1$, indicating well-ordered lamellar morphologies. (B) Experimental data for the lamellar period (d^*) and N_{bb} (circles), as well as calculated power-law fits ($d^* \sim N_{bb}^\alpha$, lines). (C) Plot of the scaling exponents (α) as a function of z . A transition occurs around $z = 0.2$ (dotted line). 68
- Scheme 3.3:** $(\text{PLA}^z\text{-}r\text{-DBE}^{1-z})_n\text{-}b\text{-}(\text{PS}^z\text{-}r\text{-DBE}^{1-z})_n$ of variable backbone degrees of polymerization ($N_{bb} = 2n = 82\text{--}533$) and grafting densities ($z = 0.75, 0.50, 0.35, 0.25, 0.15, 0.12, 0.06, \text{ and } 0.05$). 70
- Figure 3.7:** (*top*) Scheme of **System II**, comprising graft block polymers $(\text{PLA}^z\text{-}r\text{-DME}^{1-z})_n\text{-}b\text{-}(\text{PS}^z\text{-}r\text{-DBE}^{1-z})_n$ with variable total backbone degrees of polymerization ($N_{bb} = 2n$) and grafting densities (z). (A) Stacked 1D azimuthally averaged SAXS profiles for $z = 0.75$, indicating well-ordered lamellar morphologies. (B) Experimental data for the lamellar period (d^*) and N_{bb} (circles), as well as calculated power-law fits ($d^* \sim N_{bb}^\alpha$, lines). (C) Plot of the scaling exponents (α) as a function of z . A transition occurs around $z = 0.2$ (dotted line). Note that in (B) and (C),

- unfilled circles correspond to data for **System I** ($z = 1.00$), in which the side chain molecular weights are slightly higher..... 72
- Figure 3.8:** Plots of predicted N_{bb} required to access $d^* = 200$ nm as a function of grafting density (z) for (A) **System I** and (B) **System II**..... 73
- Figure 3.9:** Analysis of scaling trends with grafting density (z) for (A) **System I** and (B) **System II**. (top) Experimentally determined values and lines of best fit for the scaling exponent (α) versus z . The lines intersect at a critical z_c , associated with a transition in the backbone stiffness. In (b), the unfilled circle ($z = 1.00$) indicates data for **System I**. (bottom) Calculated root-mean-square end-to-end distances, normalized by the backbone statistical segment length (R_2/a_0), fixing $N_{bb} = 100$ 77
- Figure 3.10:** Reduced zero-shear viscosity (η_0 / a_T) versus M_w for six series with varying grafting density, z . Unentangled and entangled polymers are shown with open and filled symbols, respectively. Power-law fits are shown corresponding to Rouse (dotted line) or reptation (solid line) scaling..... 83
- Figure 3.11:** Dependence of the plateau modulus of graft polymer melts normalized by the plateau modulus of the analogous linear melt ($G_e / G_{e,lin}$) on the average backbone length between grafts (n_g). Different conformational regimes are identified as a function of n_g at constant N_{sc} . (A) Regimes predicted by Daniel et al. based on theory.⁵⁰ Adapted with permission from Nature Publishing Group. (B) Experimental data for (PLA^z-*r*-DME^{1-z})_n graft polymers. 84
- Figure 3.12:** (A) Illustration of a comb polymer at low grafting density, in which the backbone and side chain are both unperturbed Gaussian coils. The unperturbed backbone length between grafts, $L_{g,0}$, and side chain diameter, d_{sc} , are indicated. (B) Entanglement data plotted as $N_{e,bb} / N_{e,lin}$ versus d_{sc} / L_g . The black and blue lines correspond to the low- and high- z limits, respectively. When $d_{sc} / L_g > 1$, steric repulsion between the side chains reduces the density of entanglements..... 85
- Figure 3.13:** Direct comparison of the static and dynamic consequences of grafting density, z . (left axis, red) Scaling exponent α describing the change in the block polymer lamellar period with total backbone degree of polymerization ($d^* \sim N_{bb}^\alpha$). (right axis, blue) Normalized backbone degree of polymerization between entanglements ($N_{e,bb} / N_{e,lin}$). 86
- Figure 4.1:** Molecular structures and relative interaction parameters for (A) LSO and (B) LSL' brush triblock polymers. 94
- Figure 4.2:** Schematic of realistic LSO* chain dimensions used in SCFT calculations. The side chains are not expected to extend significantly more than their unperturbed end-to-end distance $R_{0,\gamma} = a_\gamma N_\gamma^{1/2}$ (where a_γ is the statistical segment length and N_γ is the degree of polymerization of $\gamma = L, S, \text{ or } O$).

- The backbone is treated as a worm-like chain of constant persistence length ξ_b and fixed contour length L 96
- Figure 4.3:** (A) TEM of LSO* stained with RuO₄. (B) Relative contrast from the stain, relative widths of corresponding layers observed by TEM, and side chain volume fractions measured by ¹H NMR. (C) One LAM₃ period with the expected ABCB domain connectivity and layer widths based on data in (B). (D) One LAM_P period observed in (A), exhibiting mesoscopic ACBC domain connectivity..... 97
- Figure 4.4:** Illustrations and SCFT data distinguishing LAM₃ and LAM_P morphologies. In A–D, the light, medium, and dark gray layers represent PLA, PS, and PEO (or mixed PLA/PEO) domains, respectively. (A, B) LSO chain packing in (A) LAM₃ and (B) LAM_P. (C, D) SCFT composition profiles for LSO* within one normalized lamellar period (z/d_0), where $\phi(z)$ is the relative segment concentration of each component. (C) $\chi_{AC} > \chi^C$: LAM₃ with $d^* = 43.5$ nm. (D) $\chi_{AC} < \chi^C$: LAM_P with $d^* = 25.6$ nm. (E) SCFT calculations of the normalized free energy (*top*) and domain spacing (*bottom*) versus $\chi_{AC} \equiv \chi_{LO}$ for LSO*. The transition from mixed (LAM_P) to unmixed (LAM₃) morphologies is first-order, occurring at a critical value χ^C (dotted line); for $\chi_{AB} = 0.080$ and $\chi_{BC} = 0.049$, $\chi^C = 0.009$ 98
- Figure 4.5:** Lamellar periods (d^*) versus normalized molecular weight for brush LSO (this work) and linear ISO and SIO triblock terpolymers (literature data). Calculated exponents (best fit) to the power law $d^* \sim M^\alpha$ are included for comparison. 100
- Figure 4.6:** Consequences of varying end block length N_X in LSL' and LSO. (A) Domain spacing d^* . (B) Apparent PLA glass transition temperatures (T_g); for all samples, a single T_g ($T_{g,PEO} < T_g \leq T_{g,PLA}$) was observed..... 101
- Figure 4.7:** Illustration of chain pullout to explain the trends in d^* for LSL' and LSO brush triblock polymers with varying end block length (equivalently, varying molecular asymmetry). Linear chains are depicted to aid visualization. As the end block length N_X increases from a fixed parent LS diblock, d^* decreases (here, $D^* \equiv d^*/d^*_{LS}$, where d^*_{LS} is the period of the parent LS diblock). (A) X = A' (LSL'): short PLA end blocks pull out of PLA domains into PS domains. (B) X = C (LSO): short PEO end blocks pull out of mixed PLA/PEO domains into PS domains. 104
- Figure 4.8:** (A) Brush LSO triblock terpolymers samples prepared for reflectivity measurements: $N_C = 8, 12, 16, 20$ (Table 4.1). (B, C) Reference samples, including (B) brush diblock copolymers (SO and LS) and (C) homopolymers of each component (*i.e.*, brush PLA, brush PS, brush PEO, and the polynorbornene backbone)..... 108
- Figure 4.9:** Representative atomic force micrographs (AFM) corresponding to spin-coated films of LSO-0 on silicon. (A) Under many conditions, the films

- dewetted, forming islands and holes. The commensurability conditions differ for brush and linear block polymers. (B) Under optimized conditions, the films wet the substrate..... 109
- Figure 4.10:** (A) Experimental (*black circles*) and simulated (*red lines*) reflectivity profiles determined for LSO-12 at three different energies: 286, 284, and 270 eV. (B) Composition profile for LSO-12 determined from reflectivity measurements. The red, green, and blue colors highlight the correspondence between each block and its SLD. 110
- Figure 4.11:** Composition profiles for LSO-12 determined by (A) fitting experimental reflectivity data or (B) SCFT. The relative segment concentrations of each component are provided over one normalized lamellar period (z / d^*). (A) Profiles were determined from RSoXR measurements at 270 eV (—), 284 eV (---), and 286 eV (.....); see Figure 4.10. (B) Profiles were calculated for PLA (*red*), PS (*green*), and PEO (*blue*). Comparison of reflectivity and SCFT profiles indicate close agreement between the measured and predicted results. 111
- Figure 4.12:** NEXAFS analysis of LSO-12 at the carbon edge. Arrows indicate transitions for PS ($C=C 1s \rightarrow \pi^*$ for the aromatic rings, $E = 284.5$ eV) and PLA ($C=O 1s \rightarrow \pi^*$ for the carbonyl, $E = 288$ eV). 112
- Figure 4.13:** SCFT composition profile for LSO-12 within one normalized lamellar period (z / d^*), where $\phi(z)$ is the relative segment concentration. Calculated profiles for PS (*green*) and the backbone (*black*) are shown; PLA and PEO are not included. (See Figure 4.11B.) A schematic illustration of midblock configurations is provided. The arrow indicates a decrease in the backbone concentration at the center of the PS domain, suggesting a large fraction of looping midblocks. 113
- Figure 4.14:** Schematic illustration of chain configurations over one lamellar period (d^*) for LSO-8 (*left*) and LSO-12 (*right*). Relevant length scales are indicated, including d^* , the thickness of the mixed PLA/PEO layers (d_{L+O}), the thickness of the PS layers (d_s), and the average distance between block junctions at the interface (a_{ij}). 114
- Figure 4.15:** (A, B) Configurations of looping midblocks inferred from reflectivity measurements for (A) LSO-8 and (B) LSO-12; see also Figure 4.14. As N_C increases from 8 to 12, the thickness of the PS domain (d_s) decreases. A concomitant increase in the average distance between block junctions at the interface (a_{ij}) is expected. (C) Like SAXS, RSoXR enables determination of d^* . However, RSoXR provides additional information due to its sensitivity to chemical composition..... 116
- Figure 5.1:** Schematic illustrations of the diverse morphologies identified for linear ABC triblock terpolymers. Variations in the block sequence and block volume fractions create an enormous parameter space for materials design..... 122

- Scheme 5.1:** Synthesis of LSO brush triblock terpolymers by ring-opening metathesis polymerization (ROMP). The block sequence, backbone lengths, and side chain lengths can be readily varied. 123
- Figure 5.2:** Ternary phase diagram for reported *linear* ABC triblock terpolymers with similar frustration (Type II) as LSO. The vertices each represent 100% pure A, B, or C by volume; moving away from a vertex in any direction represents decreasing the volume fraction of the corresponding component. The examples include linear PS-*b*-PB-*b*-PMMA and PS-*b*-P(E-*co*-B)-*b*-PMMA triblocks. 124
- Figure 5.3:** Ternary phase diagram for LSO brush triblock terpolymers. The vertices each represent 100% pure PLA (L), PS (S), or PEO (O) by volume. Each symbol represents a brush LSO triblock synthesized, annealed, and studied by SAXS. The colors indicate different morphologies: (*red*) disordered, (*green*) lamellar, (*blue*) hexagonally packed cylinders. The shapes indicate different side chain lengths: in the legend on the right, each triplet indicates [M_L , M_S , and M_O], where M_i is the number-average molecular weight (in kg/mol) of each side chain i . Unfilled symbols indicate samples that could not be unambiguously assigned by SAXS. 125
- Figure 5.4:** ABC triblock terpolymers can be classified according to the relative magnitude of χ_{AC} . (*A-C*) Each circle above represents a block, connected A-B-C from left to right. The contrast between circles represents the relative magnitude of χ ; that is, black and white is the highest-contrast pair and therefore represents the highest- χ interaction in the system. (*A*) If χ_{AC} is the smallest interaction parameter, the system experiences Type II frustration. (*B*) If χ_{AC} is larger than one of, but not both, χ_{BC} and χ_{AB} , the system experiences Type I frustration. (*C*) If χ_{AC} is the largest interaction parameter, the system is non-frustrated. 127
- Figure 5.5:** Ternary phase diagrams for (*A*) brush SLO and (*B*) brush LOS triblock terpolymers. The colors indicate different morphologies: (*red*) disordered, (*green*) lamellar, (*blue*) hexagonally packed cylinders. 128
- Figure 5.6:** SAXS data for an LSO brush triblock terpolymer ($N_A = 25$, $N_B = 22$, $N_C = 5$) obtained upon heating from 25 to 200 °C at 1 °C/min. The lamellar morphology (LAM_P) is stable throughout the entire experimentally accessible temperature range. d^* varies slightly (<5%) over this range. No order-disorder transition is observed at any temperature below the onset of decomposition. 129
- Figure 5.7:** Variable-temperature SAXS measurements for (*A*) LSO-14 and (*B*) LSO-4. Samples were heated without pressure at 2 °C/min from 25 to 200 °C, then cooled back to 25 °C at 2 °C/min. Red and blue traces correspond to measurements before and after heating, respectively. (*A*) When N_C is long, the peaks become sharper on heating, but otherwise no changes are

- observed with temperature. (B) When N_C is short, features consistent with HEX emerge on heating..... 130
- Figure 5.8:** Azimuthally integrated 1D SAXS data for an LSO triblock terpolymer ($N_A = 25$, $N_B = 22$, $N_C = 5$) annealed in four different ways: (A) Thermally annealed at 140 °C between Kapton under modest applied pressure; (B) thermally annealed at 140 °C in a DSC pan with no applied pressure; (C) dropcast from DCM onto a glass cover slip; and (D) channel-die alignment at 140 °C. SAXS data corresponding to all methods indicate the same morphology (LAM) and period (± 0.5 nm). Note that the discontinuity at $q \approx 0.065 \text{ \AA}^{-1}$ in (A) is due to a mask applied when averaging the raw 2D data. 131
- Figure 5.9:** Wide-angle X-ray scattering (WAXS) data for the PEO macromonomer (MM, *i.e.*, linear PEO), brush PLA-PS parent diblock (LSO-0), and 6 selected LSO- N_C triblock terpolymers that self-assemble to LAMP. (These data were obtained at 25°C; variable-temperature WAXS data is provided in Figure C.15.) Reflections at $2\theta = 19.1^\circ$ and 23.2° for LSO- N_C (\blacktriangledown , inset) and PEO MM match the (120) and (032) reflections from a monoclinic PEO lattice.⁴⁶ The parent diblock (LSO-0), which contains no PEO, is amorphous as expected. Crystallization is suppressed in the LSO brush triblock terpolymers compared to neat PEO. (Note: Minor peaks at 31.1° and 36.1° are artifacts present in every sample due to the geometry of the stage.)..... 133
- Figure 5.10:** Raw 2D SAXS (*left, middle*) and WAXS (*right*) data for LSO- N_C brush triblock terpolymers. The same set of samples was measured either (*left*) 3 days after annealing or (*middle, right*) 365 days after annealing.. 134
- Figure 5.11:** Changes in d^* over one year (2016–2017). $d^*(2017) / d^*(2016)$ is the ratio of d^* measured by SAXS 365 days after annealing and d^* measured 3 days after annealing. When the backbone length of the PEO block is short ($N_C \leq 12$), no significant change in d^* is observed over time. However, when N_C is long ($N_C \geq 14$), d^* decreases, concomitant with crystallization of the O blocks observed by WAXS. 138
- Figure 5.12:** Azimuthally averaged 1D WAXS data for LSO- N_C , measured 365 days after annealing. Reflections consistent with PEO crystals are observed for $N_C \geq 14$ (120 at $q = 1.36 \text{ \AA}^{-1}$; $\bar{1}32, 032, \bar{2}12, 112$ at $q = 1.67 \text{ \AA}^{-1}$). Traces have been shifted vertically for clarity. 139
- Figure 5.13:** Potential types of confined crystallization in the self-assembly of block polymers with one amorphous block and one semicrystalline block. The glass transition temperature (T_g) of the amorphous block, together with the crystallization temperature (T_c) of the crystallizable block, determine three cases for confinement (*right*): hard, soft, and crystallization-induced microphase separation. 140

- Figure 5.14:** (A) Geometry of the wide-angle X-ray scattering stage. The lamellar normal \hat{n} is parallel to \hat{z} and perpendicular to the \hat{x} - \hat{y} plane. Samples were measured with the X-ray beam along \hat{x} . (B) Fiber pattern of PEO crystals, constructed by rotating the reciprocal lattice along the c -axis. 141
- Figure 5.15:** Schematic illustrations of orientations of PEO crystallites with respect to the lamellar normal, \hat{n} . The X-ray beam is along \hat{x} , and the gray planes represent the interface between PLA/PEO and PS domains. (A) Homeotropic alignment: the c -axis of the crystals is parallel to \hat{n} . (B) Homogeneous alignment: the c -axis is perpendicular to \hat{n} . (C) Random: no preferred orientation is observed. 143
- Figure 5.16:** Comparison of the (left) 2D WAXS data along \hat{x} , (middle) PEO crystal orientation, and (right) inferred brush backbone orientation. (A) $N_C = 12$: homeotropic alignment is observed. $c \parallel \hat{n}$ suggests that the PEO block backbone is orthogonal to \hat{n} . (B) $N_C = 26$: homogeneous alignment is observed. $c \perp \hat{n}$ suggests that the PEO block backbone is parallel to \hat{n} . (C) $N_C = 30$: random orientations are observed, consistent with the HEX morphology identified by SAXS. 145
- Figure 6.1:** The wavelength of reflection (λ) increases linearly with the lamellar period (d^*), which in turn scales with the total block polymer molecular weight (M). 150
- Figure 6.2:** Predicted lamellar periods (d^*) for (A) $z = 1.0$ and (B) $z = 0.5$ block polymers with the same number of side chains ($zN_{bb} = 100$). Comparing A and B indicates that decreasing z from 1.0 to 0.5 but maintaining the same number of side chains increases d^* by 30%. 153
- Scheme 6.1:** Synthesis of block polymers with polyhedral oligomeric silsequioxane (POSS) and octadecyl (C18) side chains by sequential ROMP. 154
- Figure 6.3:** Scanning electron micrographs of cross-sections of POSS-*b*-C18 films. See Table 6.1: (A) Entry 2, (B) Entry 3, and (C) Entry 4. Ruthenium tetroxide (RuO₄) was used to preferentially stain POSS domains. 155
- Figure 6.4:** Brush block polymers self-assemble to lamellar arrays with large periods (d^*). Blending with low-molecular-weight linear homopolymers (identical to the side chains of the brush polymer) swells the structures, increasing d^* 156
- Figure 6.5:** (A) Scanning electron micrographs of cross-sections of (PLA)₁₄₃-*b*-(PS)₁₅₅ brush block polymer films with $\phi_{HP} = 0, 0.30, 0.45, 0.55, 0.65,$ and 0.68 (left to right). Below each image is a plain-view photograph showing increasing λ with increasing ϕ_{HP} . Scale bars are 500 nm. (B) d^* increases with added homopolymer (HP). d^* values were obtained by SAXS and correspond to the films in A. (C) SCFT composition profile showing the relative concentrations $[\phi(z)]$ of brush block polymer and HP segments within one normalized lamellar period (z / d^*). The profile

corresponds to the $\phi_{\text{HP}} = 0.45$ sample in *A–B*. *Blue*: PS brushes and HP; *green*: PLA brushes and HP; *red*: polynorbornene backbone. Solid lines correspond to the brush polymer, and dashed lines correspond to HPs. 157

- Figure 6.6:** Plots of d^* versus N_{bb} for graft block polymers and blends with symmetric equivalents of linear homopolymers. ϕ_{rel} is the relative backbone concentration. A (*red circles*) represents neat $z = 1.00$ block polymers ($\phi_{\text{rel}} = 1.0$, A1–A5); B (*yellow circles*) represents neat $z = 0.75$ block polymers ($\phi_{\text{rel}} = 1.3$, B1–B4); and C (*green circles*) represents neat $z = 0.50$ block polymers ($\phi_{\text{rel}} = 1.9$, C1–C4). B and C were each blended with sufficient amounts of homopolymer to dilute ϕ_{rel} to 1.0 (*unfilled triangles*). Each series was fit to a power law ($d^* \sim N_{\text{bb}}^\alpha$), and the scaling exponents α are provided in the upper right corner. 160
- Figure 6.7:** Plots of d^* versus N_{bb} for graft block polymers and blends with symmetric equivalents of linear homopolymers. ϕ_{rel} is the relative backbone concentration. B (*yellow circles*) represents neat $z = 0.75$ block polymers ($\phi_{\text{rel}} = 1.3$, B1–B4); C (*green circles*) represents neat $z = 0.50$ block polymers ($\phi_{\text{rel}} = 1.9$, C1–C4); and E (*blue circles*) represents neat $z = 0.25$ block polymers ($\phi_{\text{rel}} = 3.3$, E1–E7). C and E were each blended with sufficient amounts of homopolymer to dilute ϕ_{rel} to 1.3 (*unfilled squares*); E was also blended to reach $\phi_{\text{rel}} = 1.9$ (*unfilled diamonds*). Each series was fit to a power law ($d^* \sim N_{\text{bb}}^\alpha$), and the scaling exponents α are provided on the right. 161
- Figure 6.8:** (*left*) Schematic illustration and (*right*) chemical structure of gPS-gPEO-gPS (SOS) brush triblock copolymers. 162
- Figure 6.9:** Differential scanning calorimetry data for SOS brush triblock copolymers as functions of LiTFSI loading: (A) gPS₁₁-gPEO₇₈-gPS₁₁ and (B) gPS₁₅-gPEO₁₁₉-gPS₁₅. Traces are shown for a 5 °C/min ramp rate on heating and are shifted vertically for clarity. 164
- Figure 6.10:** Normalized ionic conductivity ($\sigma/\sigma_{\text{max}}$) for gPS₁₁-gPEO₇-gPS₁₁/LiTFSI and gPS₁₅-gPEO₁₁₉-gPS₁₅/LiTFSI blends, relative to linear PEO ($M_n = 300$ kDa). 166
- Figure 6.11:** Dynamic mechanical analysis of neat gPS₁₁-gPEO₇₈-gPS₁₁, presenting the storage (G') and loss (G'') moduli as functions of temperature and frequency (ω). 167
- Figure 6.12:** (A) Brush polymer ion gels were prepared by blending gPS-gPEO-gPS brush triblock copolymers with an ionic liquid, [BMI][TFSI]. Disordered micelles of gPS in a continuous matrix of gPEO and [BMI][TFSI] result. (B) Azimuthally averaged small-angle X-ray scattering data from four different gPS-gPEO-gPS brush block polymers at polymer concentrations $\phi_{\text{SOS}} = 0.33$. The backbone degrees of polymerization for each block are provided. Solid block lines

represent fits to a model using a hard sphere form factor and Percus-Yevick structure factor. Traces are shifted vertically for clarity.....	169
Figure 6.13: Dynamic mechanical analysis of $\phi_{\text{SOS}} = 0.16$ ion gels containing gPS ₁₅ -gPEO ₁₁₉ -gPS ₁₅ (<i>red</i>) or gPS ₃ -gPEO ₈₅ -gPS ₃ (<i>black</i>) at 25 °C, presenting the storage (G') and loss (G'') moduli as functions of frequency (ω).....	170
Figure 6.14: Ionic conductivities for brush polymer ion gels, normalized to neat [BMI][TFSI]. Closed and open symbols represent gPS ₃ -gPEO ₈₅ -gPS ₃ and gPS ₁₅ -gPEO ₁₁₉ -gPS ₁₅ samples, respectively. Polymer concentrations are 9 (□ and ■), 16 (Δ and ▲), 23 (○ and ●), and 29 wt% (◇ and ◆).....	171
Figure 6.15: Electrocatalytic reduction of CO ₂ to CO in gPS-gPEO-gPS brush polymer ion gels. The catalyst, Re(bpy)(CO) ₃ Cl, dissolves in the continuous gPEO / [BMI][TFSI] matrix.	172
Figure 6.16: Cyclic voltammetric scans of brush polymer ion gels comprising gPS ₁₅ -gPEO ₁₁₉ -gPS ₁₅ , [BMI][TFSI]. (A) Ion gels containing no additives (<i>black</i>); 14.3 mM Fc (<i>green</i>); or 14.3 mM Fc and 15.3 mM CoCp ₂ ⁺ (<i>blue</i>). (B) Ion gels containing 14.3 mM Fc and 1 atm CO ₂ (<i>black</i>); 5 mM Fc and 10 mM Re(bpy)(CO) ₃ Cl (<i>blue</i>); or 7.1 mM Fc, 14.3 mM Re(bpy)(CO) ₃ Cl, and 1 atm CO ₂ (<i>green</i>).	173
Scheme A.1: Synthesis of <i>cis</i> -5-norbornene- <i>exo</i> -dicarboxylic anhydride (A.1).	179
Scheme A.2: Synthesis of <i>N</i> -hydroxyethyl- <i>cis</i> -5-norbornene- <i>exo</i> -dicarboximide initiator (A.2).	180
Scheme A.3: Synthesis of ω -norbornenyl poly(D,L-lactide) (PLA) macromonomer.	180
Figure A.1: ¹ H NMR spectrum of PLA macromonomer in CDCl ₃	181
Scheme A.4: Synthesis of <i>N</i> -propargyl- <i>cis</i> -5-norbornene- <i>exo</i> -dicarboximide (A.3).	182
Scheme A.5: Synthesis of PS-Br (A.4) by atom-transfer radical polymerization.....	182
Scheme A.6: End group conversion: PS-Br to PS-N ₃ (A.5)	183
Scheme A.7: Synthesis of ω -norbornenyl polystyrene macromonomer (PS).	184
Figure A.2: ¹ H NMR spectrum of PS macromonomer in CDCl ₃	185
Scheme A.8: Synthesis of <i>N</i> -(hexanoic acid)- <i>cis</i> -5-norbornene- <i>exo</i> -dicarboximide (A.6).	185
Scheme A.9: Synthesis of ω -norbornenyl poly(dimethyl siloxane) macromonomer (PDMS).....	186
Figure A.3: ¹ H NMR spectrum of PDMS macromonomer in CDCl ₃	186
Scheme A.10: Synthesis of ω -norbornenyl poly(ethylene oxide) macromonomer (PEO).....	187
Figure A.4: ¹ H NMR spectrum of PEO macromonomer in CDCl ₃	187
Scheme A.11: Synthesis of <i>endo,exo</i> -norbornenyl diester diluents (1a–1d).	188

Scheme A.12: Synthesis of <i>endo,exo</i> -norbornenyl diester diluents (1e–1j).	188
Scheme A.13: Synthesis of <i>endo,endo</i> -norbornenyl diester diluents (2a–2d).	189
Scheme A.14: Synthesis of <i>exo,exo</i> -norbornenyl diester diluents (3a–3d).	190
Scheme A.15: Synthesis of <i>endo</i> -norbornenyl imide diluents (4a–4c).	190
Scheme A.16: Synthesis of <i>exo</i> -norbornenyl imide diluents (5a–5c).	191
Figure A.5: Differential scanning calorimetry (DSC) data for PS ₁₀₀ , DBE ₁₀₀ , and two copolymers thereof: (PS _{100-<i>b</i>} - DBE ₁₀₀) and (PS ^{0.5-<i>ran</i>} - DBE ^{0.5}) ₂₀₀ . The data were collected on the second heating cycle using a 10 °C/min ramp rate, and glass transition temperatures (<i>T</i> _g , open circles) were identified from the corresponding derivative curves. Both copolymers exhibit a single <i>T</i> _g between the <i>T</i> _g s of the pure components, indicating successful incorporation of both PS and DBE . The <i>T</i> _g of PS _{100-<i>b</i>} - DBE ₁₀₀ (which has a guaranteed blocky sequence) differs from the <i>T</i> _g of (PS ^{0.5-<i>ran</i>} - DBE ^{0.5}) ₂₀₀ in terms of both position and shape, suggesting that (PS ^{0.5-<i>ran</i>} - DBE ^{0.5}) ₂₀₀ is at least not blocky and instead likely random as expected.	193
Figure A.6: Stacked ¹ H NMR spectra obtained during the pyridine titration experiments. To an NMR tube containing a CD ₂ Cl ₂ solution of the monopyridine complex (11.2 mM) was titrated with a CD ₂ Cl ₂ solution containing both pyridine (1.47 M) and the monopyridine complex (11.2 mM). The concentration of the monopyridine complex remained constant during the titrations. The chemical shifts of the benzylidene ¹ H resonance was monitored at 298 K and could be employed to fit the pyridine binding constant (<i>K</i> _{binding} = 1/ <i>K</i> _{eq,1}).	195
Figure A.7: ROMP of 5a (left) and 5b (right) in CH ₂ Cl ₂ at 298 K showing the rate dependence on [G3] ₀ (maroon: [G3] ₀ = 0.5 mM, blue: [G3] ₀ = 0.05 mM, green: [G3] ₀ = 0.025 mM). The slope corresponds to the <i>k</i> _{obs} (s ⁻¹). These polymerization reactions have the same [5a] ₀ /[G3] ₀ and [5b] ₀ /[G3] ₀ ratio of 100. Time-lapse kinetic traces were obtained using our standard homopolymerization procedure.	197
Figure A.8: SEC traces for PDMS + diluent copolymerizations at full conversion.	201
Figure A.9: SEC traces for PS + diluent copolymerizations at full conversion.	202
Figure B.1: ¹ H NMR spectra of the co-monomer mixtures for each (PLA ^{0.15-<i>r</i>} - DME ^{0.85}) _n sample (Table 3.3) prior to initiation.	206
Figure B.2: SEC traces for graft block polymers BP-1 , BP-2 , and BP-3 , indicating essentially identical molecular weights and dispersities.	208
Figure B.3: ¹ H NMR data for graft block polymers BP-1 , BP-2 , and BP-3 , indicating essentially identical chemical compositions (<i>f</i> ≈ 0.5).	209
Figure B.4: Raw 2D SAXS data for System I . Compare sample IDs in Table 3.1.	210

- Figure B.5:** Raw 2D SAXS data for $z = 0.05$ graft polymers: (a) $(\text{PLA}^{0.05}\text{-}r\text{-DME}^{0.95})_{200}$, (b) $(\text{PS}^{0.05}\text{-}r\text{-DBE}^{0.95})_{200}$. These polymers correspond to each block of the lowest-grafting-density samples investigated herein. Even at large N_{bb} , no evidence of microphase separation is observed, suggesting that each block is effectively homogeneous. To a first approximation, χ between the backbone and side chains does not appear significant. 214
- Figure B.6:** Raw 2D SAXS for **System II**. Compare sample IDs in Table 3.2. 215
- Figure B.7:** SEC traces for $(\text{PLA}^z\text{-}r\text{-DME}^{1-z})_n$ graft polymers, where $z = (A) 1.00$, $(B) 0.50$, $(C) 0.40$, or $(D) 0.25$ 219
- Figure B.8:** Van Gurp-Palmen plots of the highest- M_w (*i.e.*, most-entangled) sample for each z 221
- Scheme C.1:** Synthesis of brush triblock polymers by ring-opening metathesis polymerization (ROMP): (A) LSO, (B) LSL'. Red, green, and blue structures represent poly(D,L-lactide) (L), polystyrene (S), and poly(ethylene oxide) (O) side chains, respectively. This color scheme is used in all figures. 223
- Scheme C.2:** Synthesis of LSO- N_C brush triblock terpolymers with *guaranteed* fixed N_A and N_B . A large batch of the PLA macromonomer (L MM) is polymerized by ROMP to the L brush homopolymer. Addition of the PS macromonomer (S MM) to the same flask obtains a parent LS brush diblock copolymer with controlled N_A and N_B . The solution of LS is split to 10 vials, and an appropriate volume of a stock solution of PEO macromonomer (O MM) is added to each vial. In this way, 10 different LSO brush triblock terpolymers are obtained, each with the same N_A and N_B and variable N_C . LSL' brush triblock copolymers were synthesized in the same way (replacing O MM with L MM in the last step). 224
- Figure C.1:** Size-exclusion chromatogram (SEC) of LSO* ($N_A = 28$, $N_B = 27$, $N_C = 5$). The peaks are unimodal and narrow, indicating low molar mass dispersity. Complete consumption is observed at each stage prior to addition of subsequent blocks. 226
- Figure C.2:** SEC traces of 10 LSO- N_C triblock terpolymers with fixed N_A and N_B and variable N_C . For these triblocks, $N_A = 26$, $N_B = 24$, and $0 \leq N_C \leq 20$ (Table 4.1). 226
- Figure C.3:** SEC traces of 10 LSL'- N_A' triblock copolymers with fixed N_A and N_B and variable N_A' . For these triblocks, $N_A = 30$, $N_B = 28$, and $0 \leq N_A' \leq 24$ (Table 4.2). 227
- Figure C.4:** $(A-C)$ TEM images of different sections of LSO*. (D) Higher-magnification image of one area in (C) . All images show a three-color,

- four-layer lamellar morphology with the same relative domain thicknesses and contrast. Compare Figure 4.3A. 230
- Figure C.5:** Structures and relevant domain spacings indexed by SAXS. Black and white layers represent two different domains; for simplicity in visualizing the parameters, only two domains are illustrated for lamellae (whereas LAM₃ and LAM_P each have three domains). The substrate is shown at the bottom of each sample, and the arrow indicates the direction of the X-ray beam. (A) LAM stacked normal to the beam. The relevant spacing is d^* , the lamellar period discussed in this report. (B) LAM stacked in-plane with the beam. The relevant spacing is $d_{//}$ 233
- Figure C.6:** Raw 2D SAXS data for LSO- N_C indexed (*left*) to the P1 space group along the perpendicular direction, corresponding to lamellae stacked normal to the beam (LAM_⊥) and (*right*) to the P1 space group along the parallel direction. 234
- Figure C.7:** Azimuthally integrated 1D SAXS patterns for LSO- N_C (fixed N_A , N_B and variable N_C), which obey $d^* \sim M^{-0.87}$. The large change in the position of q^* (and therefore $d^* = 2\pi/q^*$) across the series is emphasized by the gray box. All traces correspond to samples that self-assemble to majority LAM. Compare Fig. C.10 (LSL'). 237
- Figure C.8:** TEM images of (A) LSO*, (B) LSO-4, (C) LSO-10, and (D) LSO-14. All self-assemble to lamellar morphologies, consistent with SAXS. For LSO- N_C , the domain spacings were calculated by averaging over 20 periods, and the same trend is observed by TEM and SAXS. As N_C increases, d^* decreases: $d^*(\text{LSO-4}) = 19.1$ nm, $d^*(\text{LSO-10}) = 17.8$ nm, $d^*(\text{LSO-14}) = 17.7$ nm. The magnitudes of the periods are smaller than those obtained from SAXS, likely due to compression of the sample upon sectioning. The three-phase contrast is clear for LSO* but is challenging to obtain for all images. 238
- Figure C.9** Raw 2D SAXS data for LSL'- $N_{A'}$ indexed (*left*) to the P1 space group along the perpendicular direction, corresponding to lamellae stacked normal to the beam (LAM_⊥) and (*right*) to the P1 space group along the parallel direction. 240
- Figure C.10:** Azimuthally integrated 1D SAXS patterns for LSL' brush triblock copolymers with fixed N_A and N_B and variable $N_{A'}$. The LSL' series was synthesized from a common parent LS diblock in the same way as LSO with variable N_C . The large change in the position of q^* (and therefore $d^* = 2\pi/q^*$) across the series is emphasized by the gray box. All traces correspond to samples that self-assemble to majority LAM (*i.e.*, LAM₂). Compare Figure C.7 (LSO). 243
- Figure C.11:** DSC data for 10 LSO- N_C triblock terpolymers ($0 \leq N_C \leq 20$). Traces correspond to data collected upon heating from -85 °C to 120 °C at 20 °C/min. We note that under these conditions, the glass transitions of

- pure PLA, PS, and PEO are not observed. Open circles (\circ) indicate the positions of T_g , determined from the corresponding derivative curves. As N_C (and therefore the PEO content) increases, T_g decreases. Compare Fig. C.12 (LSL'). 244
- Figure C.12:** DSC data for 10 LSL'- N_A' triblock terpolymers ($0 \leq N_A' \leq 24$). Traces correspond to data collected upon heating from -85 °C to 120 °C at 20 °C/min. We note that under these conditions, the glass transition of PS is not observed. Open circles (\circ) indicate the positions of T_g , determined from the corresponding derivative curves. As N_A' increases, the T_g remains the same (± 1 °C). Compare Figure C.11 (LSO). 245
- Figure C.13:** SCFT composition profiles calculated over one lamellar period for two triblocks that self-assemble to LAMP: (A) LSO-6 and (B) LSO-20. The relative segment concentrations $\phi(z)$ of each component are shown (red: PLA, green: PS, blue: PEO). SCFT predicts a small proportion of PEO blocks mixed in PS domains when N_C is small, consistent with the chain pullout model for the unusual d^* trend. Profiles were calculated using $\chi_{LS} = 0.080$, $\chi_{SO} = 0.049$, $\chi_{LO} = -0.010$, and different C block dispersities (Table C.4). 246
- Figure C.14:** SCFT composition profiles calculated over one lamellar period for a *linear* LSO triblock terpolymer in which each block has the same molecular weight as the corresponding block in LSO*. The relative segment concentrations $\phi(z)$ of each component are shown (red: PLA, green: PS, blue: PEO). Compare Figure 4.4: both brush and linear LSO triblock terpolymers show a transition from LAM₃ to LAMP controlled by the magnitude of χ_{LO} . Profiles were calculated using $\chi_{LS} = 0.080$, $\chi_{SO} = 0.049$, and $\chi_{LO} = 0.034 = \chi^C$ (the calculated transition between LAM₃ and LAMP where each phase is equally stable). (A) For large $\chi_{LO} > \chi^C$, SCFT predicts pure domains (LAM₃). (B) For small $\chi_{LO} < \chi^C$, SCFT predicts LAMP. 247
- Figure C.15:** Variable-temperature WAXS data for (A) PEO macromonomer (MM, $M_n = 2000$ g/mol) and (B) brush triblocks LSO-4 and LSO-14. For each sample, the intensity at scattering vector $s_0 = 2\theta = 20.2^\circ$ was determined at 30 °C (before heating) and at 60 °C. At 60 °C, all samples are amorphous; the melting temperature of PEO is approximately 52 °C. The ratio of intensities at s_0 for crystalline and amorphous samples were used to estimate in the crystalline weight fractions (x_{cr}): x_{cr} in PEO MM is 50% , whereas x_{cr} in all LAMP-forming LSO samples is $<10\%$ 250

LIST OF TABLES

Table 1.1: Expressions for the relationship between the backbone stiffness (λ_b) and side chain degree of polymerization (N_{sc}). All expressions are provided for densely grafted bottlebrush polymers in a good solvent for the side chains. Note that expressions for the side chain length differ across the references (M, n, N_s, L); N_{sc} is used here to maintain consistency with the terminology in this thesis.....	3
Table 2.1: Homopolymerizations of macromonomers and diluents	21
Table 2.2: Copolymerization rate constants and reactivity ratios.	26
Table 3.1: Total number-average molecular weights (M_n) and total backbone degrees of polymerization (N_{bb}) ($\text{PLA}^z\text{-}r\text{-DME}^{1-z}$) _n - <i>b</i> -($\text{PS}^z\text{-}r\text{-DBE}^{1-z}$) _n graft block polymers (System I).....	67
Table 3.2: Total number-average molecular weights (M_n) and total backbone degrees of polymerization (N_{bb}) ($\text{PLA}^z\text{-}r\text{-DBE}^{1-z}$) _n - <i>b</i> -($\text{PS}^z\text{-}r\text{-DBE}^{1-z}$) _n graft block polymers (System II).....	71
Table 3.3: Molecular and thermal characterization data for ($\text{PLA}^z\text{-}r\text{-DME}^{1-z}$) _n graft polymers.....	82
Table 4.1: Molecular composition and characterization data for all LSO samples. Samples are identified as LSO* or LSO- N_C (fixed N_A and N_B and variable N_C). For each block i , N_i indicates the number-average degrees of polymerization through the backbone and f_i indicates the volume fraction (estimated using values in Table C.1).....	95
Table 4.2: Molecular composition and characterization data for LSL'- N_A ' series (fixed N_A and N_B and variable N_A'). For each block i , N_i indicates the number-average degrees of polymerization through the backbone and f_i indicates the volume fraction (estimated using values in Table C.1).....	95
Table 4.3: Parameters resulting from the fits to the LSO reflectivity profiles. Uncertainties represent 95% confidence intervals determined by the directed evolution Monte Carlo Markov chain algorithm.....	114
Table 6.1: Characterization data for POSS- <i>b</i> -C18 block polymers with target $x = 800$. M_w is the weight-average molecular weight, $D = M_w/M_n$ is the dispersity, and λ is the peak wavelength of reflected light. The morphologies were identified by scanning electron microscopy (SEM).....	155
Table 6.2: Graft block polymers with PLA (3230 g/mol) and PS (3990 g/mol) side chains, to be blended with linear homopolymers. The data also appear in Table 3.1.....	160
Table 6.3: Characterization data for gPS _a -gPEO _b -gPS _a brush triblock copolymers.....	164

Table 6.4: Comparison of linear and brush polymer architectures in terms of the normalized conductivity (σ/σ_{\max}) and storage modulus (G').....	169
Table A.1: SEC characterization of $(\text{PLA}^z\text{-ran-DME}^{1-z})_n$ with variable grafting densities z and backbone degrees of polymerization n	192
Table A.2: Structures and homopolymerization rate constants (k_{homo}) for all monomers synthesized and studied herein.	194
Table A.3: Compiled SEC data for PLA + diluent copolymerizations.	198
Table A.4: Kinetic data for the copolymerization of PLA (M_1 , $M_n = 3230 \text{ g mol}^{-1}$) with selected diluents (M_2). The self-propagation rate constants k_{22} and k_{11} were determined from homopolymerization experiments, and the cross-propagation rate constants k_{12} and k_{21} were determined by fitting copolymerization data using non-linear least squares regression. The reactivity ratios $r_1 = k_{11}/k_{12}$ and $r_2 = k_{22}/k_{21}$ are also provided.....	199
Table A.5: Kinetic data for the copolymerization of PDMS (M_1 , $M_n = 1280 \text{ mol}^{-1}$) with selected diluents (M_2). The self-propagation rate constants k_{22} and k_{11} were determined from homopolymerization experiments, and the cross-propagation rate constants k_{12} and k_{21} were determined by fitting copolymerization data using non-linear least squares regression. The reactivity ratios $r_1 = k_{11}/k_{12}$ and $r_2 = k_{22}/k_{21}$ are also provided.....	199
Table A.6: Kinetic data for the copolymerization of PS (M_1 , $M_n = 3990 \text{ mol}^{-1}$) with selected diluents (M_2). The self-propagation rate constants k_{22} and k_{11} were determined from homopolymerization experiments, and the cross-propagation rate constants k_{12} and k_{21} were determined by fitting copolymerization data using non-linear least squares regression. The reactivity ratios $r_1 = k_{11}/k_{12}$ and $r_2 = k_{22}/k_{21}$ are also provided.....	200
Table A.7: Compiled SEC data for PDMS + diluent copolymerizations.....	200
Table A.8: Compiled SEC data for PS + diluent copolymerizations.	201
Table B.1: Representative calculations for the grafting density of each $(\text{PLA}^{0.15}\text{-r-DME}^{0.85})_n$ sample (Table 3.3) from $^1\text{H NMR}$ analysis.	207
Table C.1: SCFT input parameters for the grafted PLA, PS, and PEO side chains: a is the statistical segment length, ρ is the bulk density, m_m is the monomer molar mass, and nv is the number of monomers per reference volume ($V_{\text{ref}} = 118 \text{ \AA}^3$). All data were obtained from literature sources ²⁻³ and reported at $140 \text{ }^\circ\text{C}$, the annealing temperature.	229
Table C.2: Glass transition temperatures (T_g), LAM spacings (d^* , $d \text{ LAM}_i$), and assigned morphologies for LSO- N_C (fixed N_A and N_B and variable N_C). See Table 4.1 for full molecular characterization data and Figures C.6–C.7 for full SAXS analysis.	233
Table C.3: Glass transition temperatures (T_g), LAM spacings (d^* , $d \text{ LAM}_i$), and assigned morphologies for LSL- N_A' (fixed N_A and N_B and variable N_A').	

See Table 4.2 for full molecular characterization data and Figures C.9–C.10 for full SAXS analysis.	239
Table C.4: SCFT calculations for the lamellar period for LSO- N_C brush triblock terpolymers, in which N_A , N_B are fixed and N_C is varied. Calculations were performed using $\chi_{LS} = 0.080$, $\chi_{SO} = 0.049$, and $\chi_{LO} = -0.010$. The decrease in d^* can be attributed to the effects of molecular asymmetry and shielding of PLA-PS interactions by the PEO block, which are further enhanced by polydispersity of the PEO block.....	246
Table C.5: SCFT calculations for the lamellar period for LSL'- $N_{A'}$ brush triblock terpolymers, in which N_A , N_B are fixed and $N_{A'}$ is varied. Calculations were performed using $\chi_{LS} = 0.080$. The decrease in d^* can be attributed to the effects of molecular asymmetry, which are further enhanced by polydispersity of the second PLA block.	247